

HiFill® PC/PBT IM 6702 UV

Techmer Polymer Modifiers - Polycarbonate + PBT

General

Material Status	• Commercial: Active
Availability	• North America
Additive	• Impact Modifier • UV Stabilizer
Features	• Impact Modified • UV Resistant
Appearance	• Colors Available
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.22		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.018	in/in	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	6300	psi	ASTM D638
Tensile Elongation (Break)	120	%	ASTM D638
Flexural Modulus	260000	psi	ASTM D790
Flexural Strength	9100	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°F, 0.125 in	12	ft·lb/in	
73°F, 0.125 in	13	ft·lb/in	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	108		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	240	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	185	°F	ASTM D648
CLTE - Flow	5.0E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	500	V/mil	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.13 in)	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	210	°F
Drying Time	4.0	hr
Rear Temperature	460 to 510	°F
Middle Temperature	460 to 510	°F
Front Temperature	460 to 510	°F
Processing (Melt) Temp	460 to 510	°F
Mold Temperature	130 to 200	°F
Back Pressure	25.0 to 60.0	psi
Screw Speed	30 to 60	rpm

