

## HiFill® J-90/30 NAT

Techmer Polymer Modifiers - Polyethylene

### General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber
Appearance	• Natural Color
Processing Method	• Injection Molding

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.17		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	8700	psi	ISO 527-2
Tensile Strain (Break)	4.0	%	ISO 527-2
Flexural Modulus	653000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	4.8	ft·lb/in	ISO 180

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	150	°F
Drying Time	1.0 to 2.0	hr
Rear Temperature	340 to 370	°F
Middle Temperature	350 to 380	°F
Front Temperature	360 to 390	°F
Nozzle Temperature	370 to 400	°F
Processing (Melt) Temp	350 to 405	°F
Mold Temperature	75 to 125	°F
Injection Rate	Slow-Moderate	
Back Pressure	0.00 to 50.0	psi
Screw Speed	Slow	

