

PRODUCT CODE	TISOPLÉN D 45 D13 R01
PRODUCT DESCRIPTION	PPC, 45% BARIUM SULPHATE FILLED, NATURAL

PHYSICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	DENSITY	-	ISO 1183	g/cm ³	1.42-1.46
	MOLDING SHRINKAGE	PARALLEL	ISO 294-4	%	0.8-1.2
	MOISTURE CONTENT	-	ISO 15512	%	<0.2

MECHANICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	YIELD STRENGTH	+23°C	ISO 527-2	MPa	15-25
	TENSILE STRESS AT BREAK	+23°C	ISO 527-2	MPa	-
	TENSILE STRAIN AT BREAK	+23°C	ISO 527-2	%	>25
	TENSILE MODULUS	+23°C	ISO 527-2	MPa	1500-2500
	IZOD IMPACT STRENGTH, NOTCHED	+23°C	ISO 180/A	kJ/m ²	6-15

THERMAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	VICAT SOFTENING TEMPERATURE	50 N	ISO 306	°C	-
	HEAT DEFLECTION TEMPERATURE	0,45 MPa	ISO 75	°C	-
	HEAT DEFLECTION TEMPERATURE	1,80 MPa	ISO 75	°C	-
	MELTING TEMPERATURE	10 K/min	ISO 11357	°C	165
	BALL PRESSURE TEST	-	ISO 60695-10-2	-	-

PRODUCT CODE	TİSOPLÉN D 45 D13 R01
PRODUCT DESCRIPTION	PPC, 45% BARIUM SULPHATE FILLED, NATURAL

ELECTRICAL & FLAMMABILITY	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	FLAME RATING	0,75 mm	UL 94	-	HB
	FLAME RATING	1,6 mm	UL 94	-	HB
	GLOW WIRE FLAMMABILITY INDEX	3 mm	IEC 60695	°C	-
	GLOW WIRE FLAMMABILITY INDEX	1,6 mm	IEC 60695	°C	-
	GLOW WIRE FLAMMABILITY INDEX	0,8 mm	IEC 60695	°C	-
	COMPARATIVE TRACKING INDEX	Solution A	ISO 60112	Volt	-
	VOLUME RESISTIVITY	-	IEC 60093	Ohm.cm	1E+15
	SURFACE RESISTIVITY	-	IEC 60093	Ohm	1E+15

INJECTION PROCESS	ÖZELLİKLERİ	BİRİM	DEĞER
	PREDRYING TEMPERATURE	°C	80
	PREDRYING TIME	Hours	1-2
	MELTING TEMPERATURE	°C	210-230
	NOZZLE TEMPERATURE	°C	230
	PRE- 3 REGION TEMPERATURE	°C	200-240
	MID-2 REGION TEMPERATURE	°C	200-240
	AFT-1 REGION TEMPERATURE	°C	150-180
	MOLD TEMPERATURE	°C	40-70
	HOLD PRESSURE	MPa	50-100