

<b>PRODUCT CODE</b>	<b>TİSLAMİD A 30D03 K04 K02 R01</b>
<b>PRODUCT DESCRIPTION</b>	<b>PA6, 30% GLASS FIBER REINFORCED, IMPACT MODIFIED, HEAT STABILIZED, NATURAL</b>

PHYSICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	DENSITY	-	ISO 1183	g/cm <sup>3</sup>	<b>1.31-1.33</b>
	MOLDING SHRINKAGE	PARALLEL/NORMAL	ISO 294-4	%	<b>0.15/0.35</b>
	MOISTURE CONTENT	-	ISO 15512	%	<b>&lt;0.2</b>

MECHANICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	YIELD STRENGTH	+23°C	ISO 527-2	MPa	-
	TENSILE STRESS AT BREAK	+23°C	ISO 527-2	MPa	<b>135-150</b>
	TENSILE STRAIN AT BREAK	+23°C	ISO 527-2	%	<b>3-4</b>
	TENSILE MODULUS	+23°C	ISO 527-2	MPa	<b>8000-9000</b>
	IZOD IMPACT STRENGTH, NOTCHED	+23°C	ISO 180/A	kJ/m <sup>2</sup>	<b>18-20</b>
	IZOD IMPACT STRENGTH, NOTCHED	-30°C	ISO 180/A	kJ/m <sup>2</sup>	<b>13-15</b>
	IZOD IMPACT STRENGTH, UNNOTCHED	+23°C	ISO 180/U	kJ/m <sup>2</sup>	<b>85-90</b>
	IZOD IMPACT STRENGTH, UNNOTCHED	-30°C	ISO 180/U	kJ/m <sup>2</sup>	<b>75-90</b>

THERMAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	VICAT SOFTENING TEMPERATURE	50 N	ISO 306	°C	<b>210</b>
	HEAT DEFLECTION TEMPERATURE	0,45 MPa	ISO 75	°C	<b>215</b>
	HEAT DEFLECTION TEMPERATURE	1,80 MPa	ISO 75	°C	<b>200</b>
	MELTING TEMPERATURE	10 K/min	ISO 11357	°C	<b>220-225</b>
BALL PRESSURE TEST	120 °C	ISO 60695-10-2	-	-	

<b>PRODUCT CODE</b>	<b>TISLAMID A 30D03 K04 K02 R01</b>
<b>PRODUCT DESCRIPTION</b>	<b>PA6, 30% GLASS FIBER REINFORCED, IMPACT MODIFIED, HEAT STABILIZED, NATURAL</b>

ELECTRICAL & FLAMMABILITY	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	FLAME RATING	0,75 mm	UL 94	-	HB
	FLAME RATING	1,6 mm	UL 94	-	HB
	GLOW WIRE FLAMMABILITY INDEX	2 mm	IEC 60695	°C	-
	GLOW WIRE IGNITABILITY TEMPERATURE	2 mm	IEC 60695	°C	-
	COMPARATIVE TRACKING INDEX	Solution A	ISO 60112	Volt	500
	VOLUME RESISTIVITY	-	IEC 60093	Ohm.cm	1E+15
	SURFACE RESISTIVITY	-	IEC 60093	Ohm	1E+13

INJECTION PROCESS	PROPERTIES	UNITS	VALUE
	PREDRYING TEMPERATURE	°C	80-110
	PREDRYING TIME	hours	3-4
	MELTING TEMPERATURE	°C	230-250
	NOZZLE TEMPERATURE	°C	210-230
	PRE- 3 REGION TEMPERATURE	°C	240-260
	MID-2 REGION TEMPERATURE	°C	240-260
	AFT-1 REGION TEMPERATURE	°C	240-260
	MOLD TEMPERATURE	°C	50-90
HOLD PRESSURE	MPa	50-100	