

POLYETHYLENE UBEC150

UBE POLYETHYLENE (Wire & Cable grade)

Properties	Features	Applications
------------	----------	--------------

Properties

Item	Unit	Nominal value	Test method
MFR	g/10min	0.23	ASTM D1238
Density	kg/m ³	919	ASTM D1505
Tensile strength	MPa	21	ASTM D638
Tensile elongation	%	650	ASTM D638
Flexural strength(Olsen)	MPa	170	ASTM D747
Hardness	(HDD)	53	ASTM D2240
Vicat softening point	°C	93	ASTM D1525
Brittle temperature	°C	<-75	ASTM D746
Volume resistivity	Ω·m	10 ¹⁴ <	ASTM D257
Dielectric constant	(1 MHz)	2.3	ASTM D1531
Dissipation factor	(1 MHz×10 ⁻³)	0.1	ASTM D1531
Dielectric strength	MV/m	36	ASTM D149

* These values are typical properties and not to be considered as specifications.
* Specimens are prepared from compression-molded sheets.

Features

- High speed extrusion

Applications

- Insulation for telephone, control, signal cables

