

UBESTA 3030JFX3

Technical Product Information

UBESTA 3030JFX3 is a plasticized and weather stabilized Polyamide 12 suitable for pneumatic tube applications with low migration properties. This material has following features:

- Low migration even at elevated temperature
- Excellent mechanical properties
- High weather resistance
- Excellent processability

Basic Properties ⁽¹⁾		Method	Unit	Value
Polymer		-	-	PA12
Colour		-	-	Natural
Density		ISO 1183-3	g/cm ³	1,01
Melting Point		ISO 11357	°C	173
MFI @ 235 °C, 2,16 Kg		ISO 1133	g/10 min	10
Shore Hardness	D scale	ISO 868	-	70
Rockwell Hardness	R scale	ISO 2039-2	-	60

Mechanical Properties ⁽²⁾		Method	Unit	Value
Tensile stress at yield		ISO 527-1,2	MPa	25
Tensile strain at yield			%	26
Tensile strain at break			%	>150
Flexural strength		ISO 178	MPa	20
Flexural modulus			MPa	400
Charpy impact strength (notched) ⁽³⁾	23 °C	ISO 179/1eA	kJ/m ²	115 P
	-40 °C		kJ/m ²	3 C

Thermal Properties ⁽²⁾		Method	Unit	Value
Temp. of deflection under load	0,45 MPa	ISO 75-2	°C	85
	1,80 MPa		°C	45
Coefficient of linear expansion		ISO 11359-2	x 10 ⁻⁴ /K	1,7

Note: All tests carried dry as mould

(1) Measured on pellets

(2) Measured on injection-moulded specimens, based on ISO type

(3) P=partial break, C=complete break



Processing conditions

	Extruder						Die
	Hopper	Zone 1	Zone 2	Zone 3	Zone 4	Adaptor	
Temperature (°C)	40 - 120	200 - 220	220 - 240	220 - 240	220 - 240	220 - 240	220 - 240

Drying conditions

UBESTA is supplied dry (moisture content < 0,1%) and packed in high barrier films. However, as polyamide is a hygroscopic material, the user should take a special care of the possible moisture absorption once the bag or liner box has been opened. In case of moisture absorption, the material should be dried with dehumidified air at 80°C for more than 4 hours.

Storage

Well-sealed packages could be stored in cool and dry conditions over long periods of time. Protect the packages from heat and direct sunlight to prevent possible damages.

