

# UBESTA 3030U

Engineering Plastics

Dry as molded

		Unit	Test method	Measured value
Melting temperature		° C	ISO 11357-3	178
Density		g/cm <sup>3</sup>	ISO 1183-3	1.02
Tensile stress at yield		MPa	ISO 527-1,2	46
Tensile strain at yield		%	ISO 527-1,2	4
Tensile strain at break		%	ISO 527-1,2	> 150
Flexural strength		MPa	ISO 178	59
Flexural modulus		MPa	ISO 178	1,450
Shore hardness	D-scale	-	ISO 868	78
Rockwell hardness	R-scale	-	ISO 2039-2	105
Impact strength (Charpy, Notched)	23 ° C	kJ/m <sup>2</sup>	ISO 179/1eA	17C
	-40 ° C	kJ/m <sup>2</sup>	ISO 179/1eA	6C
Temp. of deflection under load	0.45 MPa	° C	ISO 75-2	90
	1.8 MPa	° C	ISO 75-2	48
Moulding shrinkage (In flow direction/ In transverse direction)		%	ISO 294-4	0.6/1.5
Abrasion loss (CS-17. 1,000 rev.)		mg	ISO 9352	6
Coef. Of linear thermal expansion		10 <sup>-4</sup> /K	ISO 11359-2	1.3
Volume resistivity		Ω·cm	IEC 60093	10 <sup>15</sup>
Moisture absorption (24 h in water at 23 ° C)		%	ISO 62	0.7
Melt flow rate(235 ° C/2,160 g)		g/10 min	ISO 1133	3
Comments				General
Color				Natural

Impact Strength:N=not broken P=partially broken C=completely broken

