

POLYETHYLENE F522

UBE POLYETHYLENE (HP-LDPE)

- Properties
- Additives
- Features
- Applications

Properties

Item	Unit	Nominal value	Test method
MFR	g/10min	5	ASTM D1238
Density	kg/m ³	922	ASTM D1505
Melting point	°C	110	UBE method
Tensile strength	MPa	14	ASTM D638
Tensile elongation	%	550	ASTM D638
Flexural strength(Olsen)	MPa	150	ASTM D747
Hardness	(HDD)	52	ASTM D2240
Vicat softening point	°C	90	ASTM D1525
Brittle temperature	°C	<-75	ASTM D746

* These values are typical properties and not to be considered as specifications.
* Specimens are prepared from compression-molded sheets.

Additives

- Slip agent,Antiblocking agent, Antioxidant

Features

- Processability, Transparency, Glossiness

Applications

- Blown film
- Thin film

