

# POLYETHYLENE J2522

UBE POLYETHYLENE (HP-LDPE)

---

**Properties**   **Additives**   **Features**   **Applications**

## Properties

---

Item	Unit	Nominal value	Test method
MFR	g/10min	20	ASTM D1238
Density	kg/m <sup>3</sup>	919	ASTM D1505
Melting point	°C	109	UBE method
Tensile strength	MPa	9.5	ASTM D638
Tensile elongation	%	350	ASTM D638
Flexural strength(Olsen)	MPa	130	ASTM D747
Hardness	(HDD)	47	ASTM D2240
Vicat softening point	°C	87	ASTM D1525
Brittle temperature	°C	-42	ASTM D746

\* These values are typical properties and not to be considered as specifications.

\* Specimens are prepared from compression-molded sheets.

## Additives

---

- Additive-free

## Features

---

- Moldability, Glossiness

## Applications

---

- Injection molding
- Cap, Daily necessities

