

POLYETHYLENE F022NH

UBE POLYETHYLENE (HP-LDPE)

Properties Additives Features Applications

Properties

Item	Unit	Nominal value	Test method
MFR	g/10min	0.8	ASTM D1238
Density	kg/m ³	922	ASTM D1505
Melting point	°C	110	UBE method
Tensile strength	MPa	18	ASTM D638
Tensile elongation	%	750	ASTM D638
Flexural strength(Olsen)	MPa	160	ASTM D747
Hardness	(HDD)	54	ASTM D2240
Vicat softening point	°C	95	ASTM D1525
Brittle temperature	°C	<-75	ASTM D746

* These values are typical properties and not to be considered as specifications.

* Specimens are prepared from compression-molded sheets.

Additives

- Additive-free

Features

- Toughness, Transparency

Applications

- Blown film
- Thick film, Shrink film, L-LDPE modification

