

# POLYETHYLENE F320

UBE POLYETHYLENE (HP-LDPE)

---

**Properties**   **Additives**   **Features**   **Applications**

## Properties

---

Item	Unit	Nominal value	Test method
MFR	g/10min	3.5	ASTM D1238
Density	kg/m <sup>3</sup>	921	ASTM D1505
Melting point	°C	109	UBE method
Tensile strength	MPa	15	ASTM D638
Tensile elongation	%	550	ASTM D638
Flexural strength(Olsen)	MPa	140	ASTM D747
Hardness	(HDD)	50	ASTM D2240
Vicat softening point	°C	93	ASTM D1525
Brittle temperature	°C	<-75	ASTM D746

\* These values are typical properties and not to be considered as specifications.

\* Specimens are prepared from compression-molded sheets.

## Additives

---

- Slip agent, Antiblocking agent, Antioxidant

## Features

---

- Processability, Flexibility

## Applications

---

- Blown film
- Thin film

