



## Technical Data Sheet

### LCA® PPCO2020

### High Flow Copolymer Polypropylene

Typical Compound Properties	Value / Measure		Test Methods
<b>Physical Properties</b>			
	English Units (ISO)	Metric Units	
Melt Flow Rate @ 230 / 2.16	20 g/10 min		ASTM D-1238
Density	0.925 g/cm3	0.93 g/cm3	ASTM D-792
Ash Content	%	0 %	ASTM D-5630
Linear Mold Shrinkage	in/in	mm/mm	ASTM D-955
<b>Mechanical Properties</b>			
Izod Impact - Notched	1.8 ft-lb/in (kJ/m)	96 J/m	ASTM D-256
Tensile Strength @ Yield	3,200 psi (Mpa)	22 MPa	ASTM D-638
Tensile Strength @ Break	psi (Mpa)	0 MPa	ASTM D-638
Tensile Elongation @ Yield	%	0 %	ASTM D-638
Tensile Elongation @ Break	50 %	50 %	ASTM D-638
Flexural Strength @ Yield	psi (Mpa)	0 MPa	ASTM D-790
Flexural Stress @ Break	psi (Mpa)	0 MPa	ASTM D-790
Flexural Stress @ 5% Strain	psi (Mpa)	0 MPa	ASTM D-790
Flexural Modulus	155,000 psi (Mpa)	1,069 MPa	ASTM D-790
<b>Thermal Properties</b>			
DTUL @ 66 psi (455 kPa)	Deg. F	Deg. C	ASTM D-648
@ 264 psi (1820 kPa)	Deg. F	Deg. C	ASTM D-648
Vicat Softening Temperature	Deg. F	Deg. C	ASTM D-1525





## Technical Data Sheet

### LCA® PPCO2020

### High Flow Copolymer Polypropylene

Typical Processing Conditions			
Process Variable	Description	Values	
<b>Temperatures</b>		<b>F</b>	<b>C</b>
Barrel	Rear	360 - 400	
	Center	380 - 410	
	Front	400 - 430	
	Nozzle	400 - 430	
	Mold	70 - 120	

#### Drying

Type  
Temperature  
Time

