

# 超塑烯® UE508

## EVATHENE® UE508

### 乙稀醋酸乙稀酯共聚合樹脂



## ETHYLENE-VINYL ACETATE COPOLYMER RESINS

概述	Description
超塑烯® UE508 是一種乙稀醋酸乙稀酯共聚合物，可運用在不織布的粉末塗膠與熱熔接著。	EVATHENE® UE508 is an ethylene-vinyl acetate copolymer resin (EVA) for use in powder coating and hot melt adhesion of non-woven fabric
特性	Characteristics
<ul style="list-style-type: none"> <li>◇ 極高流動性</li> <li>◇ 黏著性強</li> <li>◇ 極佳的耐水性</li> <li>◇ 加工性極佳</li> </ul>	<ul style="list-style-type: none"> <li>◇ High flowability</li> <li>◇ Strong adhesion</li> <li>◇ Excellent water resistance</li> <li>◇ Excellent processability</li> </ul>
應用	Applications
粉末燙壓貼合 (使用於不織布熱熔膠)	Powder hot melt (for hot melt adhesion of non-woven-fabric)

### 物理性質 Physical Properties

項目 Properties	試驗方法 Test Method	數 值 Typical Value
VA 含量 VA Content (wt%)	USI	8
熔融指數 Melt Index (g/10min)	ASTM D1238	85
密度 Density (g/cm <sup>3</sup> )	ASTM D792	0.925
斷裂點抗張強度(模片) Tensile Strength(Molded) (Break) (kg/ cm <sup>2</sup> )	ASTM D638	80
斷裂點伸長率 (模片) Ultimate Elongation(Molded) (%)	ASTM D638	400
低溫脆裂溫度 Low Temperature Brittleness (°C/F50)	ASTM D746	<-76
衛氏軟化溫度 Vicat Softening Temperature (°C)	ASTM D1525	70
熔點 Melt Point (°C)	ASTM D3418	96
硬度(蕭氏 A) Hardness (Shore A)	ASTM D2240	94

