

## EUROPRENE® S-SBR

## SOL R C3743 Styrene - Butadiene Copolymer

Europrene® SOL R C3743 is a solution polymerized, oil extended styrene-butadiene random copolymer. The polymer is extended with 37.5 phr of **TDAE oil** and contains a non-staining antioxidant.

Main Properties	Test Method	Unit	Typical Value
Mooney Viscosity ML 1+4(100 °C)	ASTM D 1646	MU	75
Oil content	ASTM D 5774	% wt	27.3
Bound Styrene	Internal Method	% wt	36.5
Vinyl content	Internal Method	% wt	43 <sup>(1)</sup>
Volatile Matter	ASTM D 5668	% wt	0.75 max
Tg	Internal Method	°C	-28

<sup>(1)</sup> Referred to butadiene portion

### Key Features

Europrene® SOL R C3743 is designed to show an excellent trade-off between processability and dynamic properties.

### Main Applications

Tyre tread compounds for HP/UHP tyres. It shows excellent grip and handling performances.

### Physical Form

Brown coloured bales wrapped in easily dispersible polyethylene film.

### Packaging

Returnable metal crate, nominal net weight 990 kg; 33 kg bale, 30 bales per crate (1465 x 1150 x H1123 mm).  
On request available in wooden crate: nominal net weight 990 kg; 33 kg bale, 30 bales per crate (1490 x 1150 x H975 mm).

### Storage Conditions

Store in a vented, dry area at temperatures between 20°C and 30°C; no direct sunlight.  
Shelf life: 24 months minimum.

