



# CLEARFLEX® H&T DFH 20 BA

LLDPE  
Linear low density polyethylene bio attributed



## SUSTAINABILITY

The product Clearflex H&T DFH 20 BA 'Bio attributed' is a highly sustainable LLDPE produced using bionafta from renewable raw materials together with traditional raw materials. In order to attribute the sustainable feedstock component to the final product Versalis applies the Mass Balance approach, a recognized methodology that allows to trace the flow of materials along the value chain and to assign the sustainability characteristic of the raw material to the final product on a documentary basis. Clearflex H&T DFH 20 BA provides the same chemical composition and physical-mechanical performance of the traditional grade, in addition is accompanied by a sustainability declaration that certifies the share of bio attributed product. It is a linear low density polyethylene, butene comonomer, produced by Unipol gas phase technology and suitable for extrusion. The production of Clearflex H&T DFH 20 BA allows to contribute to the circular economy, since the bionafta used derives from waste from industrial processing of organic substances (e.g. used cooking oils). Clearflex H&T DFH 20 BA will be bio circular attributed for 85%. The exact amount of "bio attributed" product will be reported in the sustainability certificate issued upon the delivery of the product.

## MAIN PROPERTIES

Resin Properties	Value	Unit	Test method
Melt Flow Rate (190 °C/2.16 kg)	0.65	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	-	g/10min	ISO 1133
Melt Flow Rate (190 °C/21.6 kg)	44	g/10min	ISO 1133
Density	0.924	g/cm <sup>3</sup>	ISO 1183
Melting Point	120	°C	Metodo interno
Brittleness temperature	<- 60	°C	ASTM D 746
Vicat softening point (1 kg)	110	°C	ISO 306/A
Mechanical Properties *	Value	Unit	Test method
Tensile stress at yield	11	MPa	ISO 527
Tensile stress at break	15	MPa	ISO 527
Tensile strain at yield	-	%	ISO 527
Elongation at break	>800	%	ISO 527
Flexural modulus	310	MPa	ISO 178
Hardness Shore D	44	-	ISO 868 A
Falling weight**	-	J	ISO 6603-2
Izod impact strength, notched	-	J/m	ASTM D 256
Environmental Stress Cracking Resistance (ESCR)***	>500	h	ASTM D 1693(B)





CLEARFLEX® H&T LLDPE / Linear low density polyethylene bio attributed

DFH 20 BA

### MAIN APPLICATIONS

Clearflex H&T DFH 20 BA exhibits a typical wide molecular weights distribution which gives an excellent processability together with good mechanical characteristics. It is mainly designed for the production of micro-irrigation tubes, durable hoses and pipes, extruded profiles and for the production by injection molding of fittings. The outdoor use, requires the addition with anti-UV, to maintain excellent performance even after prolonged periods of exposure to sunlight.

### PROCESSING NOTES

Clearflex H&T DFH 20 BA is easily processable. Melt temperature should be between 190°C and 230°C.

### STORAGE AND HANDLING

Clearflex H&T DFH 20 BA is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletized polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practiced throughout your facility. The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight. Improper storage can initiate degradation which results in odor generation, color changes and can have negative effects on the physical properties of the product. Before using this product, it is recommended to read and understand the relevant Safety Data Sheet.

### AVAILABILITY

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

### FOOD CONTACT STATUS

Clearflex H&T DFH 20 BA complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

