



RIBLENE® FF 39 F BA

LDPE
Low density polyethylene bio attributed



SUSTAINABILITY

The product Riblene FF 39 F BA 'Bio attributed' is a highly sustainable LDPE produced using bionafra from renewable raw materials together with traditional raw materials. In order to attribute the sustainable feedstock component to the final product Versalis applies the Mass Balance approach, a recognized methodology that allows to trace the flow of materials along the value chain and to assign the sustainability characteristic of the raw material to the final product on a documentary basis. Riblene FF 39 F BA provides the same chemical composition and physical-mechanical performance of the traditional grade, in addition is accompanied by a sustainability declaration that certifies the share of bio attributed product. It is a low-density polyethylene suitable for blown film technology. The production of Riblene FF 39 F BA allows to contribute to the circular economy, since the bionafra used derives from renewable resources (e.g. vegetable oils). Riblene FF 39 F BA will be bio attributed for 100%. The exact amount of "bio attributed" product will be reported in the sustainability certificate issued upon the delivery of the product.

MAIN PROPERTIES

Resin Properties	Value	Unit	Test method
Melt Flow Rate (190 °C/2,16 kg)	0,8	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	-	g/10min	ISO 1133
Melt Flow Rate (190 °C/2,16 kg)	-	g/10min	ISO 1133
Density	0,924	g/cm ³	ISO 1183
Melting Point	111	°C	Metodo interno
Brittleness temperature	< -75	°C	ASTM D 746
Vicat softening point (1 kg)	95	°C	ISO 306/A
Film Properties *	Value	Unit	Test method
Tensile stress at yield MD	11	MPa	ISO 527-3
Tensile stress at yield TD	12	MPa	ISO 527-3
Tensile stress at break MD	22	MPa	ISO 527-3
Tensile stress at break TD	20	MPa	ISO 527-3
Elongation at break MD	400	%	ISO 527-3
Elongation at break TD	600	%	ISO 527-3
1% Secant modulus MD	180	MPa	ISO 527-3
1% Secant modulus TD	190	MPa	ISO 527-3
Elmendorf tear resistance MD	45	N/mm	ISO 6383-2
Elmendorf tear resistance TD	60	N/mm	ISO 6383-2
Impact resistance F50 (Dart Drop Test)	180	g	ISO 7765-1/A
Dynamic coefficient of friction (COF)	> 0,5	-	ISO 8295
Haze	6	%	ISO 14782
Gloss, 45°	70	%	ASTM D 2457
Recommended film thickness	30 + 120	micron	-





RIBLENE LDPE / Low density polyethylene bio attributed

FF 39 F BA

MAIN APPLICATIONS

Riblene FF 39 F BA is recommended for the production of shrink film for medium and light loads, for lamination film and for blend. Riblene FF 39 F BA is characterised by a good melt strength leading to a good bubble stability during extrusion. Films manufactured by Riblene FF 39 F BA are easily heat shrinkable and characterised by good optical and mechanical properties.

PROCESSING NOTES

Riblene FF 39 F BA is easily processable using blown film technology. Melt temperature should be between 170 °C and 200 °C. Recommended thickness: 30 - 120 µm.

STORAGE AND HANDLING

Riblene FF 39 F BA is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletized polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practiced throughout your facility. The product should be stored in dry conditions at temperatures below 50 °C and protected from sunlight. Improper storage can initiate degradation which results in odor generation, color changes and can have negative effects on the physical properties of the product. Before using this product, it is recommended to read and understand the relevant Safety Data Sheet.

AVAILABILITY

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

FOOD CONTACT STATUS

Riblene FF 39 F BA complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

