



RIBLENE® GM 20 R BCA

LDPE
Low density polyethylene bio circular attributed



SUSTAINABILITY

The product GM 20 R BCA 'Bio Circular attributed' is a highly sustainable LDPE produced using bionafta from renewable raw materials together with traditional raw materials. In order to attribute the sustainable feedstock component to the final product Versalis applies the Mass Balance approach, a recognized methodology that allows to trace the flow of materials along the value chain and to assign the sustainability characteristic of the raw material to the final product on a documentary basis. Riblene GM 20 R BCA provides the same chemical composition and physical-mechanical performance of the traditional grade, in addition is accompanied by a sustainability declaration that certifies the share of bio attributed product. It is a medium fluidity low density polyethylene resin (LDPE), obtained from vessel process. The production of Riblene GM 20 R BCA allows to contribute to the circular economy, since the bionafta used derives from waste from industrial processing of organic substances (e.g. used cooking oils). Riblene GM 20 R BCA will be bio circular attributed for 100%. The exact amount of 'bio circular attributed' product will be reported in the sustainability certificate issued upon the delivery of the product.

MAIN PROPERTIES

Resin Properties	Value	Unit	Test method
Melt Flow Rate (190 °C/2,16 kg)	3,5	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	-	g/10min	ISO 1133
Melt Flow Rate (190 °C/21,6 kg)	-	g/10min	ISO 1133
Density	0,920	g/cm ³	ISO 1183
Melting Point	111	°C	Internal Method
Brittleness temperature	< -75	°C	ASTM D 746
Vicat softening point (1 kg)	89	°C	ISO 306/A
Mechanical Properties *	Value	Unit	Test method
Tensile stress at yield	10	MPa	ISO 527
Tensile stress at break	12	MPa	ISO 527
Tensile strain at yield	520	%	ISO 527
Flexural modulus	-	MPa	ISO 178
Hardness Shore A	-	Shore A	ISO 868 A
Hardness Shore D	47	Shore D	ISO 868 A





RIBLENE LDPE / Low density polyethylene bio circular attributed

GM 20 R BCA

MAIN APPLICATIONS

Riblene GM 20 R BCA is suitable for coating applications where a low neck-in is required. Moreover, for its rheological properties, Riblene GM 20 R BCA can be used for injection moulded high thickness articles, caps, closures, stoppers and houseware.

PROCESSING NOTES

Riblene GM 20 R BCA is easily processed in extrusion coating lines. The suggested temperature is from 260 to 330 °C. Riblene GM 20 R BCA can be extruded at thickness lower than 15 µm.

STORAGE AND HANDLING

Riblene GM 20 R BCA is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletized polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practiced throughout your facility. The product should be stored in dry conditions at temperatures below 50 °C and protected from sunlight. Improper storage can initiate degradation which results in odor generation, color changes and can have negative effects on the physical properties of the product. Before using this product, it is recommended to read and understand the relevant Safety Data Sheet.

AVAILABILITY

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

FOOD CONTACT STATUS

Riblene GM 20 R BCA complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

