

## RIBLENE®

LDPE

## GM 20 R

Low density polyethylene

Riblene GM 20 R is a medium fluidity low density polyethylene resin (LDPE), obtained from vessel process.

### Main Application

Riblene GM 20 R is suitable for coating applications where a low neck-in is required. Moreover, for its rheological properties, Riblene GM 20 R can be used for injection moulded high thickness articles, caps, closures, stoppers and houseware.

### Main Properties

#### Resin Properties

	Value	Unit	Test Method
Melt Flow Rate (190 °C/2,16 kg)	3,5	g/10min	ISO 1133
Melt Flow Rate (190 °C/21,6 kg)	-	g/10min	ISO 1133
Density	0,920	g/cm <sup>3</sup>	ISO 1183
Melting Point	111	°C	Internal method
Brittleness temperature	< -75	°C	ASTM D 746 ISO
Vicat softening point (1 kg)	89	°C	306/A

#### Mechanical Properties \*

	Value	Unit	Test Method
Tensile stress at yield	10	MPa	ISO 527
Tensile stress at break	12	MPa	ISO 527
Elongation at break	520	%	ISO 527
Flexural modulus	-	MPa	ISO 178
Hardness Shore A	-	Shore A	ISO 868 A
Hardness Shore D	47	Shore D	ISO 868 A



## Processing notes

Riblene GM 20 R is easily processed in extrusion coating lines. The suggested temperature is from 260 to 330 °C. Riblene GM 20 R can be extruded at thickness lower than 15 µm.

## Storage and Handling

Riblene GM 20 R is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practised throughout your facility.

The product should be stored in dry conditions at temperatures below 50 °C and protected from sunlight. Improper storage can initiate degradation which results in odour generation, colour changes and can have negative effects on the physical properties of the product.

Before using this product it is recommended to read and understand the relevant Safety Data Sheet.

## Availability

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

## Food Contact Status

Riblene GM 20 R complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

