



versalis

## Technical Data Sheet

### EUOPRENE LATICES<sup>®</sup>

XSB Latex

### 5585

Carboxylated Styrene - Butadiene Copolymer

Europrene Latex 5585 is an aqueous dispersion of a carboxylated styrene-butadiene copolymer obtained using synthetic anionic emulsifiers. It contains a non staining antioxidant

Properties	Test Method	Unit	Typical Value
Total solid content	ASTM D1417	% wt	50
Brookfield viscosity 20 rpm, 25 C°	ASTM D1417	mPa.s	300
Styrene bound	ASTM D5775	% wt	47
pH	ASTM D1417		8,0

### Key Features

Europrene Latex 5585 shows excellent performances at high filler loading.

### Main Applications

Europrene Latex 5585 is used for primary and secondary backings when a soft handle is required

### Physical Form

Liquid, color white or milky white

### Packaging

Bulk (road tankers or flexitanks) and IBC (1000 l.)

### Storage Conditions

Store in closed vented tanks or in a covered place in sealed packaging, away from sunlight and heat sources, at temperature between +5 and +30 C°. The shelf life is 6 months minimum

