



versalis

## Technical Data Sheet

### EUOPRENE LATICES<sup>®</sup>

XSB Latex

### 8435

Carboxylated Styrene - Butadiene Copolymer

Europrene Latex 8435 is an aqueous dispersion of a carboxylated styrene-butadiene copolymer obtained using synthetic anionic emulsifiers. It contains a non staining antioxidant

Properties	Test Method	Unit	Typical Value
Total solid content	ASTM D1417	% wt	50
Brookfield viscosity 20 rpm, 25 C°	ASTM D1417	mPa.s	600
Styrene bound	ASTM D5775	% wt	69
pH	ASTM D1417		8,0

### Key Features

### Main Applications

Europrene Latex 8435 is mainly used in very firm handle carpet backsizing and needlefelt impregnation.

### Physical Form

Liquid, color white or milky white

### Packaging

Bulk (road tankers or flexitanks) and IBC (1000 l.)

### Storage Conditions

Store in closed vented tanks or in a covered place in sealed packaging, away from sunlight and heat sources, at temperature between +5 and +30 C°. The shelf life is 6 months minimum

