


**ERACLENE®  
BC 82 BA**

 HDPE  
High density polyethylene bio attributed

**SUSTAINABILITY**

The product Eraclene BC 82 BA 'Bio attributed' is a highly sustainable HDPE produced using bionafta from renewable raw materials together with traditional raw materials. In order to attribute the sustainable feedstock component to the final product Versalis applies the Mass Balance approach, a recognized methodology that allows to trace the flow of materials along the value chain and to assign the sustainability characteristic of the raw material to the final product on a documentary basis. Eraclene BC 82 BA provides the same chemical composition and physical-mechanical performance of the traditional grade, in addition is accompanied by a sustainability declaration that certifies the share of bio attributed product. It is a high density polyethylene resin with antioxidants, suitable for blow moulding application. The production of Eraclene BC 82 BA allows to contribute to the circular economy, since the bionafta used derives from renewable resources (e.g. vegetable oils). Eraclene BC 82 BA will be bio attributed for 95%. The exact amount of 'bio attributed' product will be reported in the sustainability certificate issued upon the delivery of the product.

**MAIN PROPERTIES**

Resin Properties	Value	Unit	Test method
Melt Flow Rate (190 °C/2.16 kg)	0.25	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	0.9	g/10min	ISO 1133
Melt Flow Rate (190 °C/21.6 kg)	23	g/10min	ISO 1133
Density	0.954	g/cm <sup>3</sup>	ISO 1183
Melting Point	132	°C	Metodo interno
Brittleness temperature	<- 60	°C	ASTM D 746
Vicat softening point (1 kg)	125	°C	ISO 306/A

  

Mechanical Properties *	Value	Unit	Test method
Tensile stress at yield	27	MPa	ISO 527
Tensile stress at break	30	MPa	ISO 527
Tensile strain at yield	-	%	ISO 527
Elongation at break	>600	%	ISO 527
Flexural modulus	1200	MPa	ISO 178
Hardness Shore D	64	-	ISO 868 A
Falling weight	-	J	ISO 6603-2
Izod impact strength, notched	180	J/m	ASTM D 256
Environmental Stress Cracking Resistance (ESCR)	> 60	h	ASTM D 1693(B)





ERACLENE® HDPE / High density polyethylene bio attributed

BC 82 BA

### MAIN APPLICATIONS

Eraclene BC 82 BA is especially recommended for the production of containers up to 20 liters. It is used to produce, with high-speed machines, blow moulded containers for household and industrial chemicals (detergents, bleaches, etc), cosmetics (shampoos, creams, lotions, etc). It is also suitable for thin wall items and can be extruded into profiles and sheets. It combines a good stress cracking resistance with a good rigidity and impact strength. This resin exhibits a high melt strength together with a moderate swelling. Eraclene BC 82 BA is characterized by an intermediate molecular weight distribution which balances overall performances with ease of processing.

### PROCESSING NOTES

Eraclene BC 82 BA can be processed in the latest high speed blow moulding machines with excellent results. Moulded parts exhibit outstanding surface quality. Trimming is excellent.

Typical moulding conditions:

Temperature setting, barrel zone 1: 170 - 180 (°C)

Temperature setting, barrel zone 2: 185 - 195 (°C)

Temperature setting, head and die: 185 - 195 (°C)

Operation temperature: 195 - 205 (°C)

### STORAGE AND HANDLING

Eraclene BC 82 BA is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletized polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practiced throughout your facility.

The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight. Improper storage can initiate degradation which results in odor generation, color changes and can have negative effects on the physical properties of the product. Before using this product, it is recommended to read and understand the relevant Safety Data Sheet.

### AVAILABILITY

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

### FOOD CONTACT STATUS

Eraclene BC 82 BA complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

