



ERACLENE[®] MM 80 U BCA

HDPE
High density polyethylene bio circular attributed



SUSTAINABILITY

The product Eraclene MM 80 U BCA 'Bio Circular attributed' is a highly sustainable HDPE produced using bio-nafta from renewable raw materials together with traditional raw materials. In order to attribute the sustainable feedstock component to the final product Versalis applies the Mass Balance approach, a recognized methodology that allows to trace the flow of materials along the value chain and to assign the sustainability characteristic of the raw material to the final product on a documentary basis. Eraclene MM 80 U BCA provides the same chemical composition and physical-mechanical performance of the traditional grade, in addition is accompanied by a sustainability declaration that certifies the share of bio attributed product. It is a high-density polyethylene homopolymer resin with antioxidants, suitable for injection moulding application. The production of Eraclene MM 80 U BCA allows to contribute to the circular economy, since the bio-nafta used derives from waste from industrial processing of organic substances (e.g. used cooking oils). Eraclene MM 80 U BCA will be bio circular attributed for 95%. The exact amount of "bio circular attributed" product will be reported in the sustainability certificate issued upon the delivery of the product.

MAIN PROPERTIES

Resin Properties	Value	Unit	Test method
Melt Flow Rate (190 °C/2.16 kg)	5.5	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	14	g/10min	ISO 1133
Melt Flow Rate (190 °C/21.6 kg)	-	g/10min	ISO 1133
Density	0.956	g/cm ³	ISO 1183
Melting Point	132	°C	Metodo interno
Brittleness temperature	<- 60	°C	ASTM D 746
Vicat softening point (1 kg)	127	°C	ISO 306/A
Mechanical Properties *	Value	Unit	Test method
Tensile stress at yield	27	MPa	ISO 527
Tensile stress at break	20	MPa	ISO 527
Tensile strain at yield	-	%	ISO 527
Elongation at break	550	%	ISO 527
Flexural modulus	1350	MPa	ISO 178
Hardness Shore D	69	-	ISO 868 A
Falling weight	-	J	ISO 6603-2
Izod impact strength, notched	110	J/m	ASTM D 256
Environmental Stress Cracking Resistance (ESCR)	-	h	ASTM D 1693(B)





ERACLENE® HDPE / High density polyethylene bio circular attributed

MM 80 U BCA

MAIN APPLICATIONS

The narrow molecular weight distribution and the high density make Eraclene MM 80 U BCA the ideal polymer for injection molding application. Thermal stability during the transformation phase is excellent. The manufactures produced with Eraclene MM 80 U BCA have a high rigidity and a good impact resistance.

PROCESSING NOTES

Eraclene MM 80 U BCA is readily processable by conventional injection moulding equipment with excellent results.

Typical processing conditions (*).

Temperature profile of the barrel (°C) 220 - 275

Temperature of the mould (°C) 10 - 40

(*). Processing conditions are depending on several parameters: the shape of the part to be manufactured, the localisation of the injection point, the injection moulding machine and the cooling of the mould.

STORAGE AND HANDLING

Eraclene MM 80 U BCA is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletized polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practiced throughout your facility. The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight. Improper storage can initiate degradation which results in odor generation, color changes and can have negative effects on the physical properties of the product. Before using this product, it is recommended to read and understand the relevant Safety Data Sheet.

AVAILABILITY

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

FOOD CONTACT STATUS

Eraclene MM 80 U BCA complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

