



# ERACLENE® MP 90 U BA

HDPE  
High density polyethylene bio attributed



## SUSTAINABILITY

The product Eraclene MP 90 U BA 'Bio attributed' is a highly sustainable HDPE produced using bionafta from renewable raw materials together with traditional raw materials. In order to attribute the sustainable feedstock component to the final product Versalis applies the Mass Balance approach, a recognized methodology that allows to trace the flow of materials along the value chain and to assign the sustainability characteristic of the raw material to the final product on a documentary basis. Eraclene MP 90 U BA provides the same chemical composition and physical-mechanical performance of the traditional grade, in addition is accompanied by a sustainability declaration that certifies the share of bio attributed product. It is a high-density polyethylene homopolymer resin with antioxidants, suitable for injection moulding application. The production of Eraclene MP 90 U BA allows to contribute to the circular economy, since the bionafta used derives from renewable resources (e.g. vegetable oils). Eraclene MP 90 U BA will be bio attributed for 95%. The exact amount of "bio attributed" product will be reported in the sustainability certificate issued upon the delivery of the product.

## MAIN PROPERTIES

Resin Properties	Value	Unit	Test method
Melt Flow Rate (190 °C/2.16 kg)	7.5	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	20	g/10min	ISO 1133
Melt Flow Rate (190 °C/21.6 kg)	-	g/10min	ISO 1133
Density	0.960	g/cm <sup>3</sup>	ISO 1183
Melting Point	135	°C	Metodo interno
Brittleness temperature	<- 60	°C	ASTM D 746
Vicat softening point (1 kg)	128	°C	ISO 306/A
Mechanical Properties *	Value	Unit	Test method
Tensile stress at yield	30	MPa	ISO 527
Tensile stress at break	17	MPa	ISO 527
Tensile strain at yield	-	%	ISO 527
Elongation at break	400	%	ISO 527
Flexural modulus	1450	MPa	ISO 178
Hardness Shore D	69	-	ISO 868 A
Falling weight	-	J	ISO 6603-2
Izod impact strength, notched	100	J/m	ASTM D 256
Environmental Stress Cracking Resistance (ESCR)	-	h	ASTM D 1693(B)





ERACLENE® HDPE / High density polyethylene bio attributed

MP 90 U BA

## MAIN APPLICATIONS

Eraclene MP 90 U BA has a narrow molecular weight distribution and a high density which makes it the perfect choice for manufactures requiring outstanding rigidity, warpage resistance and toughness. It is specifically designed for bottle crates, cases, toys, trays and other similar objects requiring rigidity.

## PROCESSING NOTES

Eraclene MP 90 U BA is readily processable by conventional injection moulding equipment with excellent results.

Typical processing conditions (\*)

Temperature profile of the barrel (°C) 190 - 260

Temperature of the mould (°C) 10 - 40

(\*) Processing conditions are depending on several parameters: the shape of the part to be manufactured, the localisation of the injection point, the injection moulding machine and the cooling of the mould.

## STORAGE AND HANDLING

Eraclene MP 90 U BA is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletized polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practiced throughout your facility.

The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight. Improper storage can initiate degradation which results in odor generation, color changes and can have negative effects on the physical properties of the product. Before using this product, it is recommended to read and understand the relevant Safety Data Sheet.

## AVAILABILITY

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

## FOOD CONTACT STATUS

Eraclene MP 90 U BA complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

