



ERACLENE® SB 60 BCA

HDPE
High density polyethylene bio circular attributed



SUSTAINABILITY

The product Eraclene SB 60 BCA 'Bio Circular attributed' is a highly sustainable HDPE produced using bionafta from renewable raw materials together with traditional raw materials. In order to attribute the sustainable feedstock component to the final product Versalis applies the Mass Balance approach, a recognized methodology that allows to trace the flow of materials along the value chain and to assign the sustainability characteristic of the raw material to the final product on a documentary basis. Eraclene SB 60 BCA provides the same chemical composition and physical-mechanical performance of the traditional grade, in addition is accompanied by a sustainability declaration that certifies the share of bio attributed product. It is a high density polyethylene resin with antioxidants, suitable for blow moulding application. The production of Eraclene SB 60 BCA allows to contribute to the circular economy, since the bionafta used derives from waste from industrial processing of organic substances (e.g. used cooking oils). Eraclene SB 60 BCA will be bio circular attributed for 95%. The exact amount of "bio circular attributed" product will be reported in the sustainability certificate issued upon the delivery of the product.

MAIN PROPERTIES

Resin Properties	Value	Unit	Test method
Melt Flow Rate (190 °C/2.16 kg)	-	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	0.4	g/10min	ISO 1133
Melt Flow Rate (190 °C/21.6 kg)	10	g/10min	ISO 1133
Density	0.948	g/cm ³	ISO 1183
Melting Point	130	°C	Metodo interno
Brittleness temperature	<- 60	°C	ASTM D 746
Vicat softening point (1 kg)	125	°C	ISO 306/A
Mechanical Properties *	Value	Unit	Test method
Tensile stress at yield	22	MPa	ISO 527
Tensile stress at break	31	MPa	ISO 527
Tensile strain at yield	-	%	ISO 527
Elongation at break	>800	%	ISO 527
Flexural modulus	900	MPa	ISO 178
Hardness Shore D	61	-	ISO 868 A
Falling weight	-	J	ISO 6603-2
Izod impact strength, notched	260	J/m	ASTM D 256
Environmental Stress Cracking Resistance (ESCR)	-	h	ASTM D 1693(B)





ERACLENE® HDPE / High density polyethylene bio circular attributed

SB 60 BCA

MAIN APPLICATIONS

Eraclene SB 60 BCA is recommended for the production of extruded sheets to be used as semi finished items for thermoforming and protection profiles for metallic parts. The excellent wear resistance properties and low friction allow Eraclene SB 60 BCA to be used for the preparation of technical products. Thanks to high noise absorption, the sheets produced by Eraclene SB 60 BCA can be used as acoustic insulator for barrier construction.

PROCESSING NOTES

Eraclene SB 60 BCA can be easily extruded. Due to its high flowability (low viscosity at high shear rates), Eraclene SB 60 BCA exhibits low energy consumption and good extrusion output. The recommended temperature profile is between 200 °C and 230 °C.

STORAGE AND HANDLING

Eraclene SB 60 BCA is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletized polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practiced throughout your facility. The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight. Improper storage can initiate degradation which results in odor generation, color changes and can have negative effects on the physical properties of the product. Before using this product, it is recommended to read and understand the relevant Safety Data Sheet.

AVAILABILITY

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

FOOD CONTACT STATUS

Eraclene SB 60 BCA complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

