



versalis

Technical Data Sheet

ERACLENE®

HDPE

PF 92

High density polyethylene

Eraclene PF 92 is a homopolymer high density polyethylene resin (HDPE), with antioxidants, suitable for pipe application. It is characterized by high rigidity, high impact strength and low swelling.

Eraclene PF 92 has an intermediate molecular weight distribution which perfectly balances overall performances with ease of processing.

Main Application

Eraclene PF 92 is recommended for the production of structured wall pipes when high rigidity is required. It can be used for the production of sheets and profiles.

Main Properties

Resin Properties

	Value	Unit	Test Method
Melt Flow Rate (190 °C/2.16 kg)	0.7	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	2.6	g/10min	ISO 1133
Melt Flow Rate (190 °C/21.6 kg)	45	g/10min	ISO 1133
Density	0.960	g/cm ³	ISO 1183
Melting point	138	°C	Internal method
Brittleness temperature	<- 60	°C	ASTM D 746
Vicat softening point (1 kg)	128	°C	ISO 306/A

Mechanical Properties *

	Value	Unit	Test Method
Tensile stress at yield	31	MPa	ISO 527
Tensile stress at break	30	MPa	ISO 527
Tensile strain at yield	-	%	ISO 527
Elongation at break	> 800	%	ISO 527
Flexural modulus	1500	MPa	ISO 178
Hardness Shore D	66	-	ISO 868 A
Falling Weight:	-	J/mm	ISO 6603-2
Izod impact strength, notched	-	J/m	ISO 180/A
Environmental Stress Cracking Resistance (ESCR)	-	h	ASTM 1693/B



Processing notes

Eraclene PF 92 can be processed in the latest high speed extrusion lines with excellent results.

Typical Moulding Conditions

Barrel Zone 1 Temperature Setting (°C) 170-180

Barrel Zone 2 Temperature Setting (°C) 185-195

Head and Die Temperature Setting (°C) 185-195

operation Temperature (°C) 200-220

Storage and Handling

Eraclene PF 92 is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practised throughout your facility.

The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight.

Improper storage can initiate degradation which results in odour generation, colour changes and can have negative effects on the physical properties of the product.

Before using this product it is recommended to read and understand the relevant Safety Data Sheet.

Availability

Contact the versalis sales office nearest to you regarding availability and your specific application requirements.

Food Contact Status

Eraclene PF 92 complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

