



GREENFLEX® FL 55 F BA

EVA
Ethylene vinyl acetate copolymer bio attributed



SUSTAINABILITY

The product Greenflex FL 55 F BA 'Bio attributed' is a highly sustainable EVA produced using bio-nafta from renewable raw materials together with traditional raw materials. In order to attribute the sustainable feedstock component to the final product Versalis applies the Mass Balance approach, a recognized methodology that allows to trace the flow of materials along the value chain and to assign the sustainability characteristic of the raw material to the final product on a documentary basis. Greenflex FL 55 F BA provides the same chemical composition and physical-mechanical performance of the traditional grade, in addition is accompanied by a sustainability declaration that certifies the share of bio attributed product. It is an ethylene vinyl acetate copolymer (EVA) for blown and cast film extrusion. The production of Greenflex FL 55 F BA allows to contribute to the circular economy, since the bio-nafta used derives from renewable resources (e.g. vegetable oils). Greenflex FL 55 F BA will be bio attributed for 81%. The exact amount of "bio circular attributed" product will be reported in the sustainability certificate issued upon the delivery of the product.

MAIN PROPERTIES

Resin Properties	Value	Unit	Test method
Melt Flow Rate (190 °C/2,16 kg)	2,5	g/10min	ISO 1133
Vinyl acetate content	19	%	Internal Method
Density	0,941	g/cm ³	ISO 1183
Melting Point	85	°C	Internal Method
Brittleness temperature	< -80	°C	ASTM D 746
Vicat softening point (1 kg)	58	°C	ISO 306/A
Film Properties *	Value	Unit	Test method
Tensile stress at yield MD	4,5	MPa	ISO 527-3
Tensile stress at yield TD	4	MPa	ISO 527-3
Tensile stress at break MD	30	MPa	ISO 527-3
Tensile stress at break TD	27	MPa	ISO 527-3
Elongation at break MD	560	%	ISO 527-3
Elongation at break TD	750	%	ISO 527-3
1% Secant modulus MD	45	MPa	ISO 527-3
1% Secant modulus TD	53	MPa	ISO 527-3
Elmendorf tear resistance MD	20	N/mm	ISO 6383-2
Elmendorf tear resistance TD	50	N/mm	ISO 6383-2
Impact resistance F50 (Dart Drop Test)	420	g	ISO 7765-1/A
Dynamic coefficient of friction (COF)	> 0,5	-	ISO 8295
Haze	1,5	%	ISO 14782
Gloss, 45°	85	%	ASTM D 2457
Recommended film thickness	25+ 80	micron	-
Mechanical Properties **	Value	Unit	Test method
Shore A	89	Shore A	ISO 868 A
Shore D	36	Shore D	ISO 868 A





GREENFLEX® EVA / Ethylene vinyl acetate copolymer bio attributed

FL 55 F BA

MAIN APPLICATIONS

Greenflex FL 55 F BA is recommended for the production of co-extrusion film, lamination film, stretch film, barrier film for food packaging and all those applications where the typical purity of film grades is required. Films show a low fish eyes content, high elasticity, good optical properties, good sealability at low temperatures.

PROCESSING NOTES

Greenflex FL 55 F BA can be processed by conventional blown film extrusion equipments. Operation temperature from 150 °C to 170 °C is recommended. Depending on extrusion conditions, the suggested film thickness is 25+80 µm.

STORAGE AND HANDLING

Greenflex FL 55 F BA is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletized polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practiced throughout your facility. The product should be stored in dry conditions at temperatures below 50 °C and protected from sunlight. Improper storage can initiate degradation which results in odor generation, color changes and can have negative effects on the physical properties of the product. Before using this product, it is recommended to read and understand the relevant Safety Data Sheet.

AVAILABILITY

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

FOOD CONTACT STATUS

Greenflex FL 55 F BA complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

