



GREENFLEX® HN 70 BCA

EVA
Ethylene vinyl acetate copolymer bio circular attributed



SUSTAINABILITY

The product Greenflex HN 70 BCA 'Bio Circular attributed' is a highly sustainable EVA produced using bionafta from renewable raw materials together with traditional raw materials. In order to attribute the sustainable feedstock component to the final product Versalis applies the Mass Balance approach, a recognized methodology that allows to trace the flow of materials along the value chain and to assign the sustainability characteristic of the raw material to the final product on a documentary basis. Greenflex HN 70 BCA provides the same chemical composition and physical-mechanical performance of the traditional grade, in addition is accompanied by a sustainability declaration that certifies the share of bio attributed product. It is an ethylene vinyl acetate copolymer (EVA) for compounding. The production of Greenflex HN 70 BCA allows to contribute to the circular economy, since the bionafta used derives from waste from industrial processing of organic substances (e.g. used cooking oils). Greenflex HN 70 BCA will be bio circular attributed for 72%. The exact amount of "bio circular attributed" product will be reported in the sustainability certificate issued upon the delivery of the product.

MAIN PROPERTIES

Resin Properties	Value	Unit	Test method
Melt Flow Rate (190 °C/2,16 kg)	6	g/10min	ISO 1133
Vinyl acetate content	28	%	Internal Method
Density	0,952	g/cm ³	ISO 1183
Melting Point	70	°C	Internal Method
Brittleness temperature	< -80	°C	ASTM D 746
Vicat softening point (1 kg)	41	°C	ISO 306/A
Mechanical Properties *	Value	Unit	Test method
Tensile stress at yield	3	MPa	ISO 527
Tensile stress at break	-	MPa	ISO 527
Elongation at break	> 400	%	ISO 527
Flexural modulus	20	MPa	ISO 178
Shore A	75	Shore A	ISO 868 A
Shore D	31	Shore D	ISO 868 A





GREENFLEX® EVA / Ethylene vinyl acetate copolymer bio circular attributed

HN 70 BCA

MAIN APPLICATIONS

Greenflex HN 70 BCA is a medium fluidity grade with high tack, recommended as base component for hot melt adhesives used in packaging, bookbinding and woodworking.

PROCESSING NOTES

Greenflex H 70 BCA can be processed by conventional compounding equipments. Operation temperature from 140 °C to 190 °C is recommended.

STORAGE AND HANDLING

Greenflex HN 70 BCA is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletized polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practiced throughout your facility. The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight. Improper storage can initiate degradation which results in odor generation, color changes and can have negative effects on the physical properties of the product. Before using this product, it is recommended to read and understand the relevant Safety Data Sheet.

AVAILABILITY

Contact the Versalis sales office nearest to you regarding availability and your specific application requirements.

FOOD CONTACT STATUS

Greenflex HN 70 BCA complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

