

GREENFLEX[®]

EVA

HN 70

Ethylene vinyl acetate copolymer

Greenflex HN 70 is an ethylene vinyl acetate copolymer (EVA) for compounding.

Greenflex HN 70 is a medium fluidity grade with high tack.

Main Application

Greenflex HN 70 is recommended as base component for hot melt adhesives used in packaging, bookbinding and woodworking.

Main Properties

Resin Properties

	Value	Unit	Test Method
Melt Flow Rate (190 °C/2.16 kg)	6	g/10min	ISO 1133
Vinyl acetate content	28	%	Internal method
Density	0.952	g/cm ³	ISO 1183
Melting Point	73	°C	Internal method
Brittleness temperature	<- 80	°C	ASTM D 746
Vicat softening point (1 kg)	45	°C	ISO 306/A

Mechanical Properties *

	Value	Unit	Test Method
Tensile stress at yield	2.7	MPa	ISO 527
Tensile stress at break	-	MPa	ISO 527
Elongation at break	> 400	%	ISO 527
Flexural modulus	15	MPa	ISO 178
Hardness Shore A	75	-	ISO 868 A
Hardness Shore D	31	-	ISO 868 A



Processing notes

Greenflex HN 70 can be processed by conventional compounding equipments.
Operation temperature from 140°C to 190°C is recommended.

Storage and Handling

Greenflex HN 70 is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practised throughout your facility.

The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight.

Improper storage can initiate degradation which results in odour generation, colour changes and can have negative effects on the physical properties of the product.

Before using this product it is recommended to read and understand the relevant Safety Data Sheet.

Availability

Contact the versalis sales office nearest to you regarding availability and your specific application requirements.

Food Contact Status

Greenflex HN 70 complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications.
Certificates of compliance are available upon request.

