



## Technical Data Sheet

### Europrene®

E-SBR

### 1502 F BCA

Styrene – Butadiene Copolymer Bio-Circular Attributed



Europrene® 1502 F BCA is an emulsion styrene-butadiene rubber obtained by cold polymerization using a mixture of rosin acid and fatty acid soaps as emulsifiers. A non-staining antioxidant is added during the production process.

#### Sustainability

Bio raw materials can be used in production processes together with traditional raw materials. In order to attribute sustainability characteristics to the final product, Versalis applies the **Mass Balance** approach, an acknowledged methodology that ensures that the sustainability characteristics of the alternative raw material, mixed with traditional naphtha, correspond to those of the final product. BCA products are provided with a **sustainability declaration** indicating the amount of Bio-Circular Attributed component. They guarantee identical performance, quality and properties, as they do not differ in chemical composition and physical-mechanical performance from standard products.

Main Properties	Test Method	Unit	Typical Value
Mooney Viscosity ML 1+4(100 °C)	ASTM D 1646	MU	52
Bound Styrene	ASTM D 5775	% wt	23.5
Organic Acid	ASTM D 5774	% wt	6
Soap	ASTM D 5774	% wt	0.3 max
Volatile Matter	ASTM D 5668	% wt	0.75 max
Ash	ASTM D 5667	% wt	0.5 max

The product is free from any nitrosing agent and essentially free from pre-formed nitrosamines and nitrosable substances.

#### Key Features

Europrene® 1502 F BCA is an elastomer characterized by good processability, mechanical properties and abrasion resistance. It is suitable for articles where FDA certification is required.

#### Main Applications

Articles in contact with foodstuffs.

#### Physical Form

Amber bales wrapped in easily dispersible polyethylene film.

#### Packaging

Wooden crate, nominal net weight 1050 kg; 35 kg bale, 30 bales per crate (1530 x 1145 x H1090 mm).

Returnable metal crate, nominal net weight 1260 kg; 35 kg bale, 36 bales per crate (1465 x 1150 x H1123 mm).

#### Storage Conditions

Stored in a vented, dry area at temperatures between 20°C and 30°C, with no direct sunlight.

Shelf life: 18 months minimum.

