



versalis

Technical Data Sheet

DUTRAL[®]

EP(D)M

CO 033

Ethylene - Propylene Copolymer

Dutral[®] CO 033 is an Ethylene - Propylene polymer produced by suspension polymerisation using a Ziegler-Natta Catalyst at the Ferrara production facility in Italy.
A non-staining antioxidant is added during the production process.

Main Properties

Unit

Typical Value

Mooney Viscosity ML 1+4(100 °C)	MU	30
Volatiles content	% wt	0.5 max
Ash content	% wt	0.3 max
Propylene content	% wt	28

Key Features

Dutral[®] elastomers are characterized by excellent resistance to ageing and weathering, good resistance to both high and low temperatures, low permanent set values, good resistance to a large number of chemicals.

Dutral[®] CO 033 is a semi-crystalline, low molecular weight copolymer characterized by high green strength.

Main Applications

Polymer modification, belts, cables.

Physical Form

Bales wrapped with low melting point polyethylene film; typical bale weight: 25 kg.

Packaging

Cardboard box of 750 kg containing 30 bales (1050 x 1250 x h1050 mm).

Storage Conditions

Store in dry and vented areas, avoiding temperatures above 35 °C and direct sunlight.

Shelf life : 36 months.

Advice for use:

During winter period, store the polymer in heated warehouse or at room temperature (20-25°C) for at least one week before processing in order to avoid mixing difficulties due to polymer paracrystallinity.

