



versalis

Technical Data Sheet

DUTRAL[®]

EP(D)M

TER 6235

Ethylene - Propylene - Diene Terpolymer

Dutral[®] TER 6235 is an Ethylene - Propylene - Diene polymer produced by suspension polymerisation using a Ziegler-Natta Catalyst at the Ferrara production facility in Italy.
A non-staining antioxidant is added during the production process.

Main Properties

Unit

Typical Value

Mooney Viscosity ML 1+4(125 °C)	MU	33
Volatiles content	% wt	0.5 max
Ash content	% wt	0.3 max
Propylene content	% wt	32 ⁽¹⁾
ENB content	% wt	7,4 ⁽¹⁾
Oil content	% wt	23

⁽¹⁾ Referred to polymer matrix

Key Features

Dutral[®] elastomers are characterized by excellent resistance to ageing and weathering, good resistance to both high and low temperatures, low permanent set values, good resistance to a large number of chemicals.

Dutral[®] TER 6235 is a medium-high molecular weight terpolymer of medium-high diene content, extended with 23% paraffinic oil.

Dutral[®] TER 6235 based compounds can be extended with large quantities of filler and oil, and are characterized by fast curing.

It is suitable for producing particularly soft and elastic profiles.

Main Applications

Automotive, mechanical goods, building, appliances, cables.

Physical Form

Bales wrapped with low melting point polyethylene film; typical bale weight: 25 kg.

Packaging

Cardboard box of 750 kg containing 30 bales (1050 x 1250 x h1050 mm).

Storage Conditions

Store in dry and vented areas, avoiding temperatures above 35 °C and direct sunlight.

Shelf life : 36 months.

