

## B 9 Roma

Technical Data Sheet

### ABS Resin

Sinkral® B 9 Roma is an extrusion grade ABS which exhibits excellent impact strength combined with high modulus. It keeps its excellent mechanical properties even after several re-extrusions and is therefore readily recycled.

Sinkral® B 9 Roma is also applied in injection moulding for irrigation items.

### Applications

Sinkral® B 9 Roma is widely used in the extrusion and co-extrusion of sheets that require superior mechanical properties.

This ABS is suitable in a large variety of sectors such as:

- sanitary
- automotive
- furniture edgebands and surfaces
- added to recycled material to improve mechanical properties (post end user & extrusion scraps)
- compound
- injection moulded devices for irrigation.

### Typical processing data

Extrusion:

- if processed in non-vented equipment, pre-drying the material for 2 - 4 h at 80°C is recommended;
- typical melt temperature range: 180-220°C.

Injection moulding:

- dry for 2 - 4h at 80°C
- melt temperature 220 - 250°C
- mould temperature 40 - 70°C

### Certification

✓ FMVSS 302

Sinkral® B 9 Roma, as supplied in the original packaging, by composition is compliant to some existing regulations on plastic materials intended for food contact.

### Storage

- ⚠ Store away from atmospheric agents and direct sunlight, away from sources of heat and light.
- 🕒 The product, if stored correctly, keeps its characteristics for at least fifteen months.

### General information

Sinkral® B 9 Roma is available in natural colour.



## B 9 Roma

ABS Resin

Technical Data Sheet

Property	Test Conditions	Test method	Units	Values
<b>General</b>				
Water absorption	24h - 23°C	ISO 62	%	0,3
Density	-	ISO 1183	g/cm <sup>3</sup>	1,04
<b>Rheological</b>				
Melt flow rate	220°C - 10kg	ISO 1133	g/10'	4,5
<b>Mechanical</b>				
Strain at yield	50 mm / min	ISO 527	%	2,3
Tensile stress at yield	50 mm/min	ISO 527	MPa	36
Rockwell hardness	Scala R / R Scale	ISO 2039/2	-	103
Tensile modulus	1 mm/min	ISO 527	MPa	2100
Charpy impact strength, notched	+23°C	ISO 179/1eA	kJ/m <sup>2</sup>	40
Izod impact strength, notched	+23°C - 4mm	ISO 180/1A	kJ/m <sup>2</sup>	43
Izod impact strength, notched	-30°C - 4mm	ISO 180/1A	kJ/m <sup>2</sup>	21
<b>Thermal</b>				
Coefficient of linear thermal expansion	-	ISO 11359-2	10 <sup>-5</sup> /°C	9
Thermal conductivity	-	ASTM C 177	W/(K.m)	0,17
Moulding shrinkage	-	ISO 294/4	%	0,4 ÷ 0,6
Vicat softening temperature	50 N - 50°C/h	ISO 306/B	°C	100
<b>Flammability</b>				
Flame behaviour	1,5 mm	UL 94	cl.	HB
Glow wire test (GWT)	3 mm	IEC 60695-2-10	°C	650
<b>Electrical</b>				
Dielectric constant (relative permittivity)	1000 Hz secco/dry	IEC 60250	-	3,1
Dissipation factor	1000 Hz secco/dry	IEC 60250	-	15·10E-3
Surface resistivity	secco / dry	IEC 60093	ohm	10E14
Volume resistivity	secco / dry	IEC 60093	ohm·cm	10E15
Dielectric strength	secco / dry	IEC 60243	kV/mm	30

