

STYRENICS

Sinkral® L 322 Balance BA65

 ABS
 ABS bio-attributed


SUSTAINABILITY

Bio raw materials can be used in production processes together with traditional ones. To attribute the characteristics of sustainability to the final product, Versalis applies the **Mass Balance** approach, an acknowledged chain of custody that ensures the allocation of sustainability characteristics of raw materials, to final products in a regulated and verifiable manner.

Balance® BA products are provided with a **sustainability declaration** indicating the amount of Bio Attributed component. They guarantee identical performance, quality and properties, as they do not differ in chemical composition and physical-mechanical performance from standard products.

The production of Sinkral® L 322 Balance BA65 contributes to the circular economy model since the bio-nafta comes from biological feedstock (eg. vegetable oils).

Balance® BA65 products have 65% of bio-attributed share.

PROPERTIES

General	Test Conditions	Test Method	Unit	Value
Water Absorption	24 h - 23°C	ISO 62	%	0,3
Density	-	ISO 1183	g/cm ³	1,04
Rheological				
Melt Flow Index	220 °C - 10 kg	ISO 1133	g/10'	24
Mechanical				
Strain at Yield	50 mm / min	ISO 527	%	2,8
Tensile Stress at Yield	50 mm / min	ISO 527	MPa	46
Rockwell Hardness	R Scale	ISO 2039/2	-	109
Tensile Modulus	1 mm / min	ISO 527	MPa	2400
Charpy Impact Strength, notched	+ 23 °C	ISO 179/1eA	kJ/m ²	19
Izod Impact Strength, notched	+ 23 °C - 4 mm	ISO 180/1A	kJ/m ²	20
Thermal				
Coefficient of Linear Thermal Expansion	-	ISO 11359-2	10 ⁻⁵ / °C	9
Thermal Conductivity	-	ASTM C 177	W/(K·m)	0,17
Moulding Shrinkage	-	ISO 294/4	%	0,4 ± 0,6
Vicat Softening Temperature	50 N - 50 °C/h	ISO 306/B	°C	98
Flammability				
Flame Behaviour	1,5 mm	UL 94*	cl.	HB
Glow Wire Test (GWT)	3 mm	IEC 60695-2-10	°C	650





SINKRAL® ABS bio-attributed

L 322 Balance BA65

APPLICATIONS

Sinkral® L 322 Balance BA65 is suitable for:

- Small and large Appliances
- Furnishing components
- Toys
- Cosmetics
- Metal Plating
- Electrical components

PROCESSABILITY

Injection Moulding:

- Dry for 1 - 2h at 80°C
- Melt Temperature 190 -220°C
- Mould Temperature 40 - 70°C

STORAGE

-  Store away from atmospheric agents and direct sunlight, away from sources of heat and light.
-  The product, if stored correctly, keeps its characteristics for at least fifteen months.

AVAILABILITY

To find out about the availability of the resin and for information on specific applications, please contact the nearest Versalis sales office.

FOOD DECLARATION

Sinkral® L 322 Balance BA65 as supplied in the original packaging, by composition is compliant to some existing regulations on plastic materials intended for food contact.

