



# NORDEL™ IP 4570

## Hydrocarbon Rubber

### Overview

NORDEL™ IP 4570 Hydrocarbon Rubber is an amorphous ethylene-propylene-diene terpolymer (EPDM) grade designed for extruded applications. It is ideally suited for dense extruded profiles, coolant hoses, and general-purpose moldings. The combination of high viscosity and low crystallinity allows for good balance of processability, extensibility, low-temperature properties, and performance.

#### Main Characteristics:

- Amorphous
- Medium diene
- High molecular weight
- Good low temperature properties

- Complies with

U.S. FDA 21 CFR 177.2600,  
 U.S. FDA 21 CFR 177.1520 (See NOTES 1),  
 U.S. FDA 21 CFR 175.105 (See NOTES 2),  
 U.S. FDA 21 CFR 177.1210.  
 Consult the regulations for complete details.

#### Applications:

- Extruded profiles
- Coolant hoses

#### NOTES:

- (1) Can be used in contact with all foods except water in oil emulsions, high or low fat, and low moisture fats and oil.  
 (2) Adhesives only.

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.860 g/cm <sup>3</sup>	0.860 g/cm <sup>3</sup>	ASTM D297
Ethylene Content	50.0 wt%	50.0 wt%	ASTM D3900
Ethylidene Norbornene (ENB) Content	5.0 wt%	5.0 wt%	ASTM D6047
Mooney Viscosity (ML 1+4, 257°F (125°C))	70 MU	70 MU	ASTM D1646
Ash Content	< 0.1 wt%	< 0.1 wt%	ASTM D296
Molecular Weight Distribution	Medium	Medium	Dow Method
Propylene Content	45.0 wt%	45.0 wt%	ASTM D3900
Residual Transition Metal	< 10 ppm	< 10 ppm	Dow Method
Volatile Matter	< 0.40 wt%	< 0.40 wt%	Dow Method

### Additional Information

#### Storage and Handling:

The quality of EPDM products may be affected by exposure to artificial or natural light. This product should be stored indoors in its original packaging and out of direct sunlight.

### Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

