



EVERCAP™ DMDA-1232 NT 7

High Density Polyethylene Resin

Overview

EVERCAP™ DMDA-1232 NT 7 High Density Polyethylene Resin enables the right performance properties to meet demanding closure and fitment application needs. It is intended for use in both compression and injection molded closure applications. This resin has been designed to deliver increased flexibility over higher density resins, while maintaining good processing characteristics beneficial to molders. Typical applications include molded beverage closures.

Main Characteristics:

- Unique Stiffness/Flexibility Balance
 - Excellent Processing Characteristics
- 1,000 ppm Slip

Complies with:

- U.S. FDA 21 CFR 177.1520(c)3.1a.
- Canadian HPFB No Objection
- European Commission Regulation (EU) No 10/2011

Consult the regulations for complete details.

Additive

- Antiblock: No
- Slip: 1000 ppm
- Processing Aid: No

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.945 g/cm ³	0.945 g/cm ³	ASTM D792
Melt Index (190°C/2.16 kg)	20 g/10 min	20 g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (ESCR)			ASTM D1693
122°F (50°C), 10% Igepal, F50	6.00 hr	6.00 hr	
122°F (50°C), 100% Igepal, F50	17.0 hr	17.0 hr	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength			ASTM D638
Yield	3310 psi	22.8 MPa	
Break	2700 psi	18.6 MPa	
Tensile Elongation			ASTM D638
Yield	11 %	11 %	
Break	800 %	800 %	
Flexural Modulus - 2% Secant	123000 psi	848 MPa	ASTM D790
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	62	62	ASTM D2240
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature	252 °F	122 °C	ASTM D1525
Melting Temperature (DSC)	262 °F	128 °C	Dow Method
Peak Crystallization Temperature (DSC)	239 °F	115 °C	Dow Method

Additional Information

Molded and tested in accordance with ASTM D 4976.

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

