



# DOW™ LDPE 133A

## Low Density Polyethylene Resin

### Overview

- A medium anti-block resin for heavy duty film applications
- Optimum gauge range: 2.0-6.0 mil
- Used for thick gauge film applications

Complies with:

- U.S. FDA 21 CFR 177.1520 (c) 2.2.
- Canadian HPFB No Objections (With Limitations)
- EU, No 10/2011

Consult the regulations for complete details.

### Additive

- Antiblock: 3000 ppm
- Slip: No
- Processing Aid: No

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.923 g/cm <sup>3</sup>	0.923 g/cm <sup>3</sup>	ASTM D792
Base Density <sup>1</sup>	0.921 g/cm <sup>3</sup>	0.921 g/cm <sup>3</sup>	Dow Method
Melt Index (190°C/2.16 kg)	0.25 g/10 min	0.25 g/10 min	ASTM D1238
Films	Nominal Value (English)	Nominal Value (SI)	Test Method
Film Thickness - Tested	2 mil	51 µm	
Film Puncture Resistance (2.0 mil (51 µm))	44.0 ft-lb/in <sup>3</sup>	3.64 J/cm <sup>3</sup>	Dow Method
Film Toughness			ASTM D882
MD : 2.0 mil (51 µm)	1630 ft-lb/in <sup>3</sup>	135 J/cm <sup>3</sup>	
TD : 2.0 mil (51 µm)	2250 ft-lb/in <sup>3</sup>	186 J/cm <sup>3</sup>	
Tensile Strength			ASTM D882
MD : Yield, 2.0 mil (51 µm)	1930 psi	13.3 MPa	
TD : Yield, 2.0 mil (51 µm)	1690 psi	11.6 MPa	
MD : Break, 2.0 mil (51 µm)	3600 psi	24.8 MPa	
TD : Break, 2.0 mil (51 µm)	3820 psi	26.4 MPa	
Tensile Elongation			ASTM D882
MD : Break, 2.0 mil (51 µm)	330 %	330 %	
TD : Break, 2.0 mil (51 µm)	620 %	620 %	
Dart Drop Impact (2.0 mil (51 µm))	250 g	250 g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 2.0 mil (51 µm)	300 g	300 g	
TD : 2.0 mil (51 µm)	200 g	200 g	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature	203 °F	95.0 °C	ASTM D1525
Melting Temperature (DSC)	232 °F	111 °C	Dow Method
Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Gloss (45°, 2.00 mil (50.8 µm))	46	46	ASTM D2457
Haze (2.00 mil (50.8 µm))	14.0 %	14.0 %	ASTM D1003
Extrusion	Nominal Value (English)	Nominal Value (SI)	
Melt Temperature	419 °F	215 °C	



---

**Extrusion Notes**

---

## Fabrication Conditions For Blown Film:

- Screw Size: 2.5 in. (63.5 mm); 30:1 L/D
- Screw Type: Single Flight Double Mix
- Die Gap: 40 mil (1.0 mm)
- Melt Temperature: 419°F (215°C)
- Output: 10 lb/hr/in. of die circumference
- Die Diameter: 6 in.
- Blow-Up Ratio: 2.5:1
- Screw Speed: 99 rpm
- Frost Line Height: 30 in. (762 mm)

**Notes**

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

---

<sup>1</sup> Base density is estimated using the assumption that every 1000 ppm of antiblock in the finished product raises the density of the polymer by 0.0006 g/cm<sup>3</sup>. Base density is the estimated density of the polymer if it did not contain any antiblock.

