



DOWLEX™ 2032 Polyethylene Resin

Overview

- Linear Low Density Polyethylene
- Complies with U.S. FDA 21 CFR 177.1520 (c) 3.2a
- Complies with Canadian HPFB No Objection (With Limitations)
- Complies with EU, No 10/2011
- Complies with Japan Hygienic Olefin and Styrene Plastics Association
- Consult the regulations for complete details.

Additive

- Antiblock: No
- Slip: No
- Processing Aid: No

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.926 g/cm ³	0.926 g/cm ³	ASTM D792
Base Density ¹	0.926 g/cm ³	0.926 g/cm ³	Dow Method
Melt Index (190°C/2.16 kg)	2.0 g/10 min	2.0 g/10 min	ASTM D1238
Films	Nominal Value (English)	Nominal Value (SI)	Test Method
Film Thickness - Tested	1 mil	25 µm	
Film Puncture Resistance (1.0 mil (25 µm))	220 ft·lb/in ³	18.2 J/cm ³	Dow Method
Film Toughness			ASTM D882
MD : 1.0 mil (25 µm)	3080 ft·lb/in ³	255 J/cm ³	
TD : 1.0 mil (25 µm)	2760 ft·lb/in ³	228 J/cm ³	
Tensile Strength			ASTM D882
MD : Yield, 1.0 mil (25 µm)	1750 psi	12.0 MPa	
TD : Yield, 1.0 mil (25 µm)	1720 psi	11.9 MPa	
MD : Break, 1.0 mil (25 µm)	9330 psi	64.3 MPa	
TD : Break, 1.0 mil (25 µm)	5100 psi	35.2 MPa	
Tensile Elongation			ASTM D882
MD : Break, 1.0 mil (25 µm)	470 %	470 %	
TD : Break, 1.0 mil (25 µm)	680 %	680 %	
Dart Drop Impact (1.0 mil (25 µm))	120 g	120 g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 1.0 mil (25 µm)	320 g	320 g	
TD : 1.0 mil (25 µm)	680 g	680 g	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature	228 °F	109 °C	ASTM D1525
Melting Temperature (DSC)	255 °F	124 °C	Dow Method
Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Gloss (45°, 1.00 mil (25.4 µm))	91	91	ASTM D2457
Haze (1.00 mil (25.4 µm))	2.10 %	2.10 %	ASTM D1003

Extrusion Notes

Fabrication Conditions For Cast Film:

- Screw Size: 2 in. (51 mm); 30:1 L/D
- Screw Size: 2.5 in. (63.5 mm); 30:1 L/D
- Screw Size: 2.5 in. (63.5 mm); 30:1 L/D
- Screw Size: 2.5 in. (63.5 mm); 30:1 L/D
- Screw Size: 2 in. (51 mm); 30:1 L/D
- Die Gap: 25 mil (0.6 mm)
- Chill Roll Temperature: 70°F (21°C)
- Melt Temperature: 525°F (274°C)
- Line Speed: 600 fpm (183 m/min)



Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

¹ Base density is estimated using the assumption that every 1000 ppm of antiblock in the finished product raises the density of the polymer by 0.0006 g/cm³. Base density is the estimated density of the polymer if it did not contain any antiblock.

