



## Technical Data Sheet

### DOWLEX™ GM 8370G Precision Packaging Resin

#### Description

DOWLEX™ GM 8370G Polyethylene Packaging Resin is a medium density resin that provides excellent optical properties and is designed for use in a variety of blown film applications needing both stiffness and good optics.

#### Complies with

- U.S. FDA 21 CFR 177.1520(c)3.2a
- EU, No 10/2011

Consult the regulations for complete details.

#### Additive

- Antiblock: No
- Processing Aid: No
- Slip: No

#### Properties<sup>1</sup>

Physical	Nominal Value	Unit (English)	Nominal Value	Unit (SI)	Test Method <sup>2</sup>
Density	0.935	g/cm <sup>3</sup>	0.935	g/cm <sup>3</sup>	ASTM D792
Melt Index (190°C/2.16 kg)	0.75	g/10 min	0.75	g/10 min	ASTM D1238
<b>Films</b>					
Film Thickness - Tested	2.0	mil	50	µm	
Film Puncture Resistance	109	ft-lb/in <sup>3</sup>	9.02	J/cm <sup>3</sup>	Internal Method
Tensile Strength					ASTM D882
MD: Yield	2602	psi	18.0	MPa	
TD: Yield	2980	psi	20.6	MPa	
MD: Break	7660	psi	52.8	MPa	
TD: Break	6860	psi	47.3	MPa	
Tensile Elongation					ASTM D882
MD: Break	720	%	720	%	
TD: Break	780	%	780	%	
Dart Drop Impact	170	g	170	g	ASTM D1709A
Elmendorf Tear Strength					ASTM D1922
MD	120	g	120	g	
TD	420	g	420	g	
<b>Thermal</b>					
Vicat Softening Temperature	252	°F	122	°C	ASTM D1525
Melting Temperature (DSC)	257	°F	125	°C	Internal Method

1. Typical properties: these are not to be construed as specifications. Users should confirm the results by their own tests.

2. ASTM: American Society for Testing and Materials



## Properties (Cont.)

Optical	Nominal Value	Unit (English)	Nominal Value	Unit (SI)	Test Method
Gloss (45°)	56		56		ASTM D2457
Haze	13.1	%	13.1	%	ASTM D1003

### Extrusion Notes

Fabrication Conditions:

- Die Diameter: 8 in
- Die Gap: 70 mil
- Melt Temperature: 451°F
- Output: 9.9 lb/hr/in. of die circumference
- Screw Size: 3.5 in.
- Blow-up Ratio: 2.5 to 1
- Screw Speed: 57 rpm
- Frost Line Height: 35 in
- Polymer processing aid was added during film fabrication

