



Experimental XUS 59910.08 Experimental Polyethylene Resin

Overview Blown and cast extrusion process. Monolayer and co-extrusion film for packaging applications. Critical for BOPE application.

Complies with:

- U.S.FDA FCN 424

Consult the regulations for complete details.

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.926 g/cm ³	0.926 g/cm ³	ASTM D792
Melt Index (190°C/2.16 kg)	1.7 g/10 min	1.7 g/10 min	ASTM D1238

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

