



VERSIFY™ 3000 Plastomer

Overview

VERSIFY™ 3000 Plastomer is a resin with a medium melt flow rate, therefore making it a general purpose film resin. It is suitable for cast film, blown film, and BOPP. It is an excellent sealant and is particularly suitable for use in BOPE structures. It has excellent compatibility with PP and is an useful agent to bring softness and temperature performance.

Main Characteristics

- Pellet
- Medium Melt Flow Rate
- Good sealant
- Compatible with PP
- Soft polypropylene

Applications

- Blown Film
- Cast Film
- BOPE
- BOPP
- Sealant

Complies with:

- EU, No 10/2011
- U.S. FDA FCN 909
- U.S. FDA 21 CFR 175.105(c)
- Consult the regulations for complete details.

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.891 g/cm ³	0.891 g/cm ³	ASTM D792
Melt Mass-Flow Rate (230°C/2.16 kg)	8.0 g/10 min	8.0 g/10 min	ASTM D1238
Total Crystallinity	44 %	44 %	Dow Method
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Break, Compression Molded)	3960 psi	27.3 MPa	ASTM D638
Tensile Elongation ¹			ASTM D638
Break, Compression Molded	730 %	730 %	
Flexural Modulus - 1% Secant (Compression Molded)	56500 psi	389 MPa	ASTM D790
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness ²			ASTM D2240
Shore A, Compression Molded	96	96	
Shore D, Compression Molded	60	60	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Glass Transition Temperature	6.80 °F	-14.0 °C	Dow Method
Vicat Softening Temperature	221 °F	105 °C	ASTM D1525
Melting Temperature (DSC)	226 °F	108 °C	Dow Method
Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Gardner Gloss			ASTM D523
20°, 39.4 mil (1000 µm), Compression Molded	126	126	
60°, 39.4 mil (1000 µm), Compression Molded	134	134	
Haze (78.7 mil (2000 µm), Injection Molded)	9.10 %	9.10 %	ASTM D1003

