

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Shore Hardness			ISO 868
Shore A, Compression Molded	92	92	
Shore D, Compression Molded	40	40	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature	180 °F	82.0 °C	ISO 306/120
Melting Temperature	207 °F	97.0 °C	DSC
Peak Crystallization Temperature (DSC)	176 °F	80.0 °C	DSC

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

¹ Compression Molded

² Compression Molded, No break

³ Rotational Molded, No break

