



APPEEL™ 1181

Peelable Resin

General Information

Product Description APPEEL™ 1181 is a modified ethylene vinyl acetate resin designed to function as a sealing layer for lidding applications. It is most often suggested to provide peelable seals over a broad temperature range to a number of container materials including PP, PET, PS and aluminum. It will also provide destruct seals to PVC and PE. APPEEL™ 1181 is available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyethylene resins.

Status

Material Status Commercial: Active

Typical Characteristics

Uses Lidding Sealant
Features High clarity and low seal initiation temperature.

Characteristics / Benefits Contains amide slip agent
Contains antiblock agent

Typical Properties

Physical	Nominal Values	Test Method(s)	
*Density ()	0.96 g/cm ³	ASTM D792	ISO 1183
*Melt Flow Index (190°C/2.16kg)	8.9 g/10 min	ASTM D1238	ISO 1133
Thermal	Nominal Values	Test Method(s)	
*Melting Point (DSC)	75 °C (167 °F)	ASTM D3418	ISO 3146
Vicat Softening Point ()	49 °C (120.2 °F)	ASTM D1525	ISO 306

Heat Seal Evaluation The performance of any sealant resin should be evaluated within the context of the application. The sealant is designed to bond to particular substrate(s). Many variables can affect seal strength, including the physical properties of the substrate being sealed to, thickness, flange or surface design, heat seal temperature, dwell time and pressure. The condition and type of the sealing equipment used, such as roller sealers versus platen seal mechanisms can make a significant difference.

In most cases sealant peel strength is used as a measure of performance. Although this is a convenient test, peel strength is affected not only by substrate adhesion but also by peel angle, separation rate, ambient temperature, tensile and modulus properties of the materials, and often by the time elapsed since the formation of the bond.

If sealant peel strength is used as a measure of sealant performance, it is imperative that peel strength be evaluated not only at the time of initial heat sealing the lid to the substrate, but throughout the life of the product and under all the conditions to which the sealant will be exposed. Only then does peel strength provide a reliable indication of adhesive performance in the specific application.

Processing Information

*Maximum Processing Temperature 235 °C (455 °F)

General Processing Information If the process is stopped for short periods of time, the screw for the APPEEL™ extruder should be kept turning at a low rpm to keep material flowing.
After processing APPEEL™, purge the material out using a polyethylene resin,



preferably with a lower melt flow rate than the APPEEL™ resin in use. The "Disco Purge Method" is suggested as the preferred purging method, as this method usually results in a more effective purging process. Information on the Disco Purge Method can be obtained via your Dow Sales Representative.

Never shut down the extrusion system with APPEEL™ in the extruder and die. Properly purge out the APPEEL™ with a polyethylene, and shut down the line with polyethylene or polypropylene in the system.

Extrusion Coating/Lamination Processing Information

Nominal Values

Extrusion Coating: The melt temperature of APPEEL™ 1181 should be maintained in the 210 - 235°C range in extrusion coating processes. Selection of a specific melt temperature will depend on screw configuration, potential power limitations, and the need to match melt viscosities. However, melt temperatures above 238C (460F) should be avoided because of possible thermal degradation of the resin.

Following is an example for suggested temperature profile on the high side of the processing range. Lower temperatures in the final metering zone, adapter and die are suggested if compatible with the process and application.

Feed Zone	135 °C (275 °F)
Second Zone	185 °C (365 °F)
Third Zone	210 °C (410 °F)
Fourth Zone	235 °C (455 °F)
Fifth Zone	235 °C (455 °F)
Adapter Zone	235 °C (455 °F)
Die Zone	235 °C (455 °F)

FDA Status Information

APPEEL™ 1181 resin complies with Food and Drug Administration Regulation 21 CFR 177.1350 - - Ethylene-vinyl acetate copolymers, subject to the limitations and requirements therein. This Regulation describes polymers that may be used in contact with food, subject to the finished food-contact article meeting the extractive limitations under the intended conditions of use, as shown in paragraph (d) of 21 CFR 177.1330.

The information and certifications provided herein are based on data we believe to be reliable, to the best of our knowledge. The information and certifications apply only to the specific material designated herein as sold by Dow and do not apply to use in any process or in combination with any other material. They are provided at the request of and without charge to our customers. Accordingly, Dow cannot guarantee or warrant such certifications or information and assumes no liability for their use.

Regulatory Information

In Europe a diversity of regulations apply in various countries. In addition, constant changes linked to the effort of their harmonization under the umbrella of European Union Directive can be observed. This makes it impossible to accurately describe the food contact status in this brochure. Updated statements describing the situation in the various European countries can be obtained through your local sales representative.

