



InLube® LCPTF15

PRODUCT DESCRIPTION 15% PTFE LUBRICATED, LIQUID CRYSTAL POLYMER (LCP)

MATERIAL STATUS Commercial: Active

AVAILABILITY Africa & Middle East, Asia Pacific, Europe, Latin America, North America

ADDITIVE PTFE Lubricant: 15%

FEATURES Chemical Resistant, Good Mold Release, Low Friction, Lubricated, Wear Resistant

USES Aerospace Applications, Battery Cases, Connectors, Electrical/Electronic Applications, Engineering Parts, Industrial Applications, Metal Replacement, Military/Defense Applications, Semiconductor Applications

FORMS Pellets

PROCESSING METHOD Injection Molding

PHYSICAL	NOMINAL VALUE	UNIT	TEST METHOD
Density / Specific Gravity	1.46	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.0 to 0.10	%	ASTM D955
MECHANICAL	NOMINAL VALUE	UNIT	TEST METHOD
Tensile Modulus	10700	MPa	ASTM D638
Tensile Strength	114	MPa	ASTM D638
Tensile Elongation (Yield)	1.5 to 2.0	%	ASTM D638
Flexural Modulus	9650	MPa	ASTM D790
Flexural Strength	124	MPa	ASTM D790
IMPACT	NOMINAL VALUE	UNIT	TEST METHOD
Notched Izod Impact (3.18 mm)	120	J/m	ASTM D256
THERMAL	NOMINAL VALUE	UNIT	TEST METHOD
Deflection Temperature Under Load 1.8 MPa, Unannealed	256	°C	ASTM D648
INJECTION	NOMINAL VALUE	UNIT	TEST METHOD
Drying Temperature	149	°C	
Drying Time	6.0 to 8.0	hr	
Suggested Max Moisture	0.010	%	
Processing (Melt) Temp	335 to 360	°C	
Mold Temperature	93 to 163	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	

NOTES

¹ Typical properties: these are not to be construed as specifications.

