



Sevrene® 4000-50A

MATERIAL STATUS Commercial: Active

AVAILABILITY North America

FEATURES Block Copolymer

APPEARANCE Colors Available

PHYSICAL	NOMINAL VALUE	UNIT	TEST METHOD
Density	1.17	g/cm ³	ISO 1183/A
ELASTOMERS	NOMINAL VALUE	UNIT	TEST METHOD
Tensile Stress ² (100% Strain)	1.50	MPa	ISO 37
Tensile Stress ² (Break)	5.70	MPa	ISO 37
Tensile Elongation ² (Break)	540	%	ISO 37
Tear Strength ³	22.6	kN/m	ISO 34-1
Compression Set			ASTM D395B
23°C, 22 hr	21	%	
70°C, 22 hr	34	%	
HARDNESS	NOMINAL VALUE	UNIT	TEST METHOD
Shore Hardness (Shore A, 15 sec)	48		ISO 868

NOTES

¹ Typical properties: these are not to be construed as specifications.

² Type 1

³ Method B, Angle

