



Oleflex™ 6261-85A-8843

MATERIAL STATUS Commercial: Active

AVAILABILITY North America

APPEARANCE Black

PHYSICAL	NOMINAL VALUE	UNIT	TEST METHOD
Density	1.12	g/cm ³	ISO 1183
ELASTOMERS	NOMINAL VALUE	UNIT	TEST METHOD
Tensile Stress (100% Strain)	4.00	MPa	ISO 37
Tensile Stress (Break)	9.50	MPa	ISO 37
Tensile Elongation (Break)	690	%	ISO 37
Tear Strength	39.9	kN/m	ISO 34-1
Compression Set (70°C, 22 hr)	57	%	ISO 815
HARDNESS	NOMINAL VALUE	UNIT	TEST METHOD
Shore Hardness (Shore A, 15 sec)	88		ISO 868
ADDITIONAL INFORMATION	NOMINAL VALUE	UNIT	TEST METHOD
Fog Test - 6h ²	98	%	SAE J1756

NOTES

¹ Typical properties: these are not to be construed as specifications.

² 85°C heating, 31°C cooling

