



## Oleflex™ 6261-70A; 307105

**MATERIAL STATUS** Commercial: Active

**AVAILABILITY** North America

PHYSICAL	NOMINAL VALUE	UNIT	TEST METHOD
Density	1.17	g/cm <sup>3</sup>	ISO 1183

  

ELASTOMERS	NOMINAL VALUE	UNIT	TEST METHOD
Tensile Stress (100% Strain)	1.90	MPa	ISO 37
Tensile Stress (Break)	1.90	MPa	ISO 37
Tensile Elongation (Break)	260	%	ISO 37
Tear Strength	17.7	kN/m	ISO 34-1

  

HARDNESS	NOMINAL VALUE	UNIT	TEST METHOD
Shore Hardness (Shore A, 15 sec)	68		ISO 868

**NOTES**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

