

XYRON™ AG213

Asahi Kasei Corporation - Polyamide + PPE

General Information
Product Description

 Modified PPE
 PA/PPE alloy
 30% Filler reinforced Non-Flame retardant

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • Asia Pacific • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PA66+PPE-GF30<

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.33	g/cm ³	ISO 1183
Molding Shrinkage ² (0.118 in)	0.30 to 1.0	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 73°F)	22000	psi	ISO 527
Tensile Strain (Break, 73°F)	3.0	%	ISO 527
Flexural Modulus (73°F)	1.26E+6	psi	ISO 178
Flexural Stress (73°F)	34500	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ³ (73°F)	5.2	ft·lb/in ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	486	°F	ISO 75-2/B
CLTE - Flow (-22 to 149°F)	1.3E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (-22 to 149°F)	4.9E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (73°F)	4.7E+15	ohms·cm	IEC 60093
Dielectric Constant			IEC 60250
100 Hz	3.50		
1 MHz	3.40		
Dissipation Factor			IEC 60250
100 Hz	5.0E-3		
1 MHz	0.010		

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Hot Air Dryer	230 to 266	°F
Drying Time - Hot Air Dryer	2.0 to 4.0	hr
Processing (Melt) Temp	536 to 572	°F
Mold Temperature	140 to 248	°F

Injection Notes

Recommended processing (melt) temperature of XYRON™ Polyamide + PPE is 280-300°C. Lower temperatures may lead to local degradation in properties due to non-uniform plasticization, while higher temperatures tend to cause silver streaking, other appearance problems and decomposition.

