

Electrafil® PA6 G/CF30 L BK

 Techmer Polymer Modifiers - *Polyamide 6*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Carbon Fiber, 30% Filler by Weight
Additive	• Lubricant
Features	• Lubricated
Appearance	• Black
Processing Method	• Injection Molding

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.33		ASTM D792
Mechanical			
Tensile Modulus	1.96E+6	psi	ASTM D638
Tensile Strength (Yield)	24700	psi	ASTM D638
Tensile Strength (Break)	24600	psi	ASTM D638
Tensile Elongation (Break)	2.6	%	ASTM D638
Impact			
Notched Izod Impact (0.125 in)	1.7	ft·lb/in	ASTM D256
Thermal			
Deflection Temperature Under Load (264 psi, Unannealed)	402	°F	ASTM D648
Electrical			
Surface Resistivity	1.0E+2 to 1.0E+6	ohms	ASTM D257

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	180	°F
Drying Time	2.0 to 3.0	hr
Rear Temperature	470 to 500	°F
Middle Temperature	480 to 510	°F
Front Temperature	490 to 520	°F
Nozzle Temperature	500 to 530	°F
Processing (Melt) Temp	480 to 525	°F
Mold Temperature	100 to 200	°F
Injection Rate		Slow
Back Pressure	0.00 to 50.0	psi
Screw Speed		Slow-Moderate

