

**HiFill® PA6 0368 BB**

 Techmer Polymer Modifiers - *Polyamide 6*
**General Information**
**General**

Material Status	<ul style="list-style-type: none"> <li>Commercial: Active</li> </ul>
Availability	<ul style="list-style-type: none"> <li>North America</li> </ul>
Processing Method	<ul style="list-style-type: none"> <li>Injection Molding</li> </ul>

**Properties <sup>1</sup>**

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	787000	psi	ASTM D638
Tensile Strength (Yield)	8500	psi	ASTM D638
Tensile Strength (Break)	8500	psi	ASTM D638
Tensile Elongation (Break)	1.6	%	ASTM D638

  

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	0.80	ft·lb/in	ASTM D256

**Processing Information**

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 3.0	hr
Rear Temperature	470 to 500	°F
Middle Temperature	480 to 510	°F
Front Temperature	490 to 520	°F
Nozzle Temperature	500 to 530	°F
Processing (Melt) Temp	480 to 525	°F
Mold Temperature	100 to 200	°F
Injection Rate	Slow	
Back Pressure	0.00 to 50.0	psi
Screw Speed	Slow-Moderate	

