

HiFill® PA6 GF20 SL1 RD PMS200

 Techmer Polymer Modifiers - *Polyamide 6*
General Information
General

Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> North America
Filler / Reinforcement	<ul style="list-style-type: none"> Glass Fiber, 20% Filler by Weight
Appearance	<ul style="list-style-type: none"> Red
Processing Method	<ul style="list-style-type: none"> Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.26		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.02E+6	psi	ASTM D638
Tensile Strength (Yield)	18600	psi	ASTM D638
Tensile Strength (Break)	18300	psi	ASTM D638
Tensile Elongation (Break)	3.9	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.6	ft·lb/in	ASTM D256

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	500 to 580	°F
Middle Temperature	500 to 580	°F
Front Temperature	500 to 580	°F
Nozzle Temperature	500 to 580	°F
Processing (Melt) Temp	460 to 535	°F
Mold Temperature	160 to 180	°F
Injection Rate	Moderate-Fast	
Back Pressure	0.00 to 50.0	psi

Notes
¹ Typical properties: these are not to be construed as specifications.
